

## TECHNICAL DATA SHEET

# ISOLBLOK

Waterproofing protective paint



### PRODUCT DESCRIPTION

Transparent, water-repellent protective, siloxane-based coating for the protection of porous building materials. Protects the substrate from water infiltration, preserving its initial appearance. Particularly suitable for terraces.

### INTENDED USE

#### Destination:

Interiors  
Exteriors

#### Specific for:

Floors and  
vertical surfaces

### SURFACE PREPARATION

The correct surface preparation of the substrate will guarantee the best results in terms of product yield, appearance, and resistance in time of the finish.

#### NEW UNPAINTED SURFACES

Clean the surface and remove all possible traces of dust or dirt.

#### Additional information:

- The substrates must in every case be sound, dry, and clean.
- Remove all possible traces of dust, dirt, or other impurities before the application.
- The nature of the support can change the final appearance of the product.

## INSTRUCTION FOR USE






### Tools used for application

- Brush
- Roller
- Spraying equipment

### APPLICATION METHOD

It is recommended to apply the product wet on wet until the substrate is completely saturated.

## TECHNICAL SPECIFICATIONS

	Indicative spread rate per coat (m <sup>2</sup> /ℓ)	-	-	Variable in relation to the absorption of the wood
	Thinning (%)	-	water	Ready to use
	Density (kg/ℓ, ±0.02)	ISO 2811	at 20°C	1.000
	Viscosity DIN 4 (s)	ISO 2555	at 20°C	38 to 42
<b>pH</b>	pH value (±0.5)	-	-	7.5
	Solid contents by weight (% , ±1)	-	-	5

\*the data herein reported refer to measures made at the end of the production process.

## TOOL CLEANING

- Clean working tools immediately after use with soap and water.

## WARNING AND ADDITIONAL INFORMATION

- Do not apply with air and surface temperatures below 5°C and above 28°C.
- The drying times indicated may vary in relation to the relative humidity and the existing temperature.
- Carefully verify spread rates and the surface area to be coated to avoid running short of product during the working process. This will also reduce the risk of eventual differences in tones.
- The spread rates and yields of the product are given as guidance only and may vary notably according to the substrate condition and the application method used.
- Stir the product thoroughly before use.
- Remove tapes before total drying of the product.
- It is recommended to always carry out a sample test on the specific surface before starting the final work.

## HANDLING AND STORAGE

- Consult the relative **Safety Data Sheet** for the detailed user's health and safety information.
- Use the product in accordance with your current health and safety legislation regulations in force.
- Do not disperse the packaging in the environment
- Store the undiluted product, in original well sealed containers, in a cool and dry area, sheltered from frost and sources of heat.
- Always protect the product from freezing.

The information reported herein is the result of our best experience and technical knowledge to date and is given in good faith and for guidance only. ADICOLOR cannot be held responsible for the actual use of the product since the application is influenced by many factors and is carried out beyond our control. The data and information herein may be subject to changes, even without notice, as a result of any technical development.

This technical data sheet cancels and replaces any existing previous version.